IN THE CLAIMS

Please amend the claims as follows:

19. (Currently amended): A silica-soda-lime glass composition comprising the following components:

SiO_2	55-75%
Na_2O	~~4.5-10~~ 2-8%
CaO	7-12%
Al_2O_3	0-7%
ZrO_2	0-8%
K_2O	0-8%
MgO	0-5%
B_2O_3	0-3%

wherein the glass composition has a ÿ ø coefficient of between 0.5 and 0.85 $N/(mm^2 \cdot °C)$, a working point of less than 1200°C, a thermal expansion coefficient $\alpha_{20\text{-}300}$ of between 60 and 88 x $10^{-7}°C^{-1}$, and a strain point of greater than 570°C.

20. (Previously Presented) The composition of claim 19 which has a softening point of greater than 750°C.

23. (Previously Presented) The composition of claim 19, wherein the working point is less than 1190°C, the softening point is at least 805°C, the thermal expansion coefficient is between 75.6 and 85 X $10^{-7}°C^{-1}$, and the strain point is between 580 and 590°C.

24. (Previously Presented) The composition of claim 19 wherein the ø coefficient satisfies the relationship

$$0.7\ MPa^2/°C^2 < \alpha^2 \cdot c/a < 2\ MPa^2/°C^2.$$

25. (Previously Presented) The composition of claim 19, comprising the following components:

SiO_2	55-75%
Na_2O	5-10%
CaO	8-12 %
$A1_2O_3$	0-7%
ZrO_2	0-8%
K_2O	0-8%.

26. (Currently Amended) The composition of claim 19, comprising the following components:

SiO_2	55-75%
Na_2O	~~4.5~~ 2-8%
K_2O	~~2.9~~ 2-8%
CaO	~~7~~ 4-11%
Al_2O_3	0-7%
ZrO_2	0-8%
MgO	0-5%.

27. (Previously Presented) The composition of claim 19 comprising the following components:

SiO2	55-75%
ZrO_2	3-8%
Na_2O	4.5-8%
K_2O	3.5-7.5%
CaO	7-11%
Al_2O_3	0-5%.

28. (Amended) The composition of claim 19, comprising the following components:

SiO_2	64.5-75%
ZrO_2	3-7.5%
Na_2O	5-9%
K_2O	3.5-7.5%
CaO	5-11%
SrO	3-7%
Al_2O_3	0-1%
MgO	0-2%
BaO	0-1.5%.

29. (Previously Presented) The composition of claim 19, wherein ø is between 0.75 and 0.84, and having an electrical resistivity such that log $\rho_{(250°)}$ is greater than 6.6.

30. (Previously Presented) The composition of claim 29 wherein the electrical resistivity is such that log $\rho_{(250°)}$ is greater than 8.

31. (Previously Presented) An article comprising the glass composition of claim 19.

32. (Previously Presented) The article of claim 31 in the form of a monolithic glazing panel, a plasma-screen substrate, an electroluminescent-screen or a cold-cathode-screen substrate.

33. (Previously Presented) The composition of claim 19, wherein the sum of the SiO_2, ZrO_2, and Al_2O_3 contents is from 71.5% to 75% by weight.